

# CLICK WOOD / HERRINGBONE

		CLICK WOOD HERRINGBONE
CONSTRUCTION / CONSTRUCTION / COSTRUZIONE / CONSTRUCTIE		1.5 MM LVT + 4 MM ISOCORE + 1 MM IXPE PAD
THICKNESS / EPAISSEUR TOTALE / SPESSORE / TOTALE DIKTE		6.50 MM
WEAR LAYER / COUCHE D'USURE / STRATO D'USURA / SLIJTLAAG		0.55 MM
UTILIZATION CLASS / CLASSE D'USAGE / CLASSE D'UTILIZZO / GEBRUIKERSKLASSE		CLASSE 33 CLASSE 42
COATING / PROTECTION / RIVSTIMENTO / BESCHERMING		PU WITH CERAMIC BEAD - ULTRAFRESH
EMBOSSING / STRUCTURE / STRUTTURA / STRUCTUUR		TRU-WOOD
BEVELLED / BISEAUTÉ / BISELLATURA / V-GROEF		YES
PLANK SIZE / DIMENSIONS DE LA LAME / DIMENSIONI / AFMETING PER PANEEL		120 X 720 MM
CARTON PACKING / EMBALLAGES EN CARTON / SCATOLE / KARTONNEN VERPAKKING		2.07 M <sup>2</sup> 24 PLANKS
PALLET PACKING / BOÎTES PAR PALETTE / NR SCATOLE À PALETTA / DOZEN PER PALLET		82.8 M <sup>2</sup> / 40 CARTONS
NET-GROSS WEIGHT PER PALLET / POIDS NET-BRUT PAR PALETTE / PESO NETTO - LORDO À PALETTA / GEWICHT NETTO - BRUTO PER PALLET		592 KG / 602 KG
IMPACT SOUND INSULATION / ISOLATION ACOUSTIQUE / ISOLAMENTO ACUSTICO / GELUIDSREDUCTIE	ISO 717-2	 21 DB
CASTO CHAIR RESISTANCE / ESSAI DE LA CHAISE À ROULETTES / PROVA CON POLTRONA A ROTELLE / ROLWEERSTAND BUREAUSTOEL	EN ISO 4918 - EN 425	 NO DAMAGE
EFFECT OF FURNITURE LEG / EFFECT DE PIED DE MEUBLE / EFFETTO DI GAMBE MOBILI / EFFECT VAN MEUBILAIR POTEN	EN 424	NO DAMAGE
THERMAL RESISTANCE / RÉSISTANCE THERMIQUE / RESISTENZA TERMICA / THERMISCHE WEERSTAND	EN ISO 12524	 0.0621 M <sup>2</sup> K/W
ELECTROSTATIC PERFORMANCE / POTENTIEL DE CHARGE ELECTROSTATIQUE / POTENZIALE DI CARICA ELETTROSTATICA / ELEKTROSTATISCHE EIGENSCHAPPEN	EN 1815	 - 2.0 KV
SLIP RESISTANCE / ANTIDÉPARANT / RESISTENZA ALLO SCIVOLAMENTO / SLIPWEERSTAND	DIN 51130	PASSES GRADE R10
WEAR RESISTANCE / RÉSISTANCE D'USURE / RESISTANCE ALL'USURA / SLIJTVASTHEID	EN 660-2	 > 4000 CYCLES
IMPACT RESISTANCE / RESISTANCE AUX CHOCS / RESISTENZA ALL'URTO / SLAGVASTHEID	EN 13329+AI	 1450 MM
LOCKING STRENGHT / FORCE DE VERROUILLAGE / FORZA DI BLOCCAGGIO / KLIKVASTHEID	ISO 24334	 LONG SIDE - 1.32 KN/M SHORT SIDE - 2.23 KN/M
RESIDUAL INDENTATION / POINÇONNEMENT RÉMANENT / SENSIBILITÀ DI IMPRESSIONE / INDRUKGEVOELIGHEID	EN ISO 24343-I	 < 0.20 MM
DIMENSIONAL STABILITY / STABILITÉ DIMENSIONNELLE / STABILITÀ DIMENSIONALE / DIMENSIONALE STABILITEIT	EN 434	 0.10%
FIRE RATING / CLASSIFICATION AU FEU / CLASSIFICAZIONE AL FUOCO / BRANDKLASSE	EN ISO 9239-I	 BFL-S1
FORMALDEHYDE EMISSION / EMISSION DE FORMALDEHYDE / EMISSIONE DI FORMALDEIDE / FORMALDEHYDE EMISSIE		CLASS E1
WARRANTY FOR DOMESTIC USE / PÉRIODE DE GARANTIE USAGE DOMESTIQUE / GARANZIA PER USO DOMESTICO / GARANTIEPERIODE HUISHOUELIJK GEBRUIK		25 YEARS
WARRANTY FOR COMMERCIAL USE / PÉRIODE DE GARANTIE USAGE COMMERCIAL / GARANZIA PER USO COMMERCIALE / GARANTIEPERIODE COMMERCIEEL GEBRUIK		10 YEARS