

CLICK WOOD RIGICORE 5.0

CONSTRUCTION / CONSTRUCTION / COSTRUZIONE / CONSTRUCTIE

TOTAL THICKNESS / EPAISSEUR TOTALE / SPESSORE / TOTALE DIKTE

WEAR LAYER / COUCHE D'USURE / STRATO D'USURA / SLIJTLAG

UTILIZATION CLASS / CLASSE D'USAGE / CLASSE D'UTILIZZO / GEBRUIKERSKLASSE

COATING / PROTECTION / RIVESTIMENTO / BESCHERMING

EMBOSSING / STRUCTURE / STRUTTURA / STRUCTUUR

BEVELLED / BISEAUTÉ / BISELLATURA / V-GROEF

PLANK SIZE / DIMENSIONS DE LA LAME / DIMENSIONI / AFMETING PER PANEEL

CARTON PACKING / EMBALLAGES EN CARTON / SCATOLE / KARTONNEN VERPAKKING

PALLET PACKING / BÔTES PAR PALETTE / NR SCATOLE À PALETTE / DOZEN PER PALLET

NET - GROSS WEIGHT PER PALLET / POIDS NET-BRUT PAR PALETTE
/ PESO NETTO - LORDO À PALETTE / GEWICHT NETTO - BRUTO PER PALLET

CASTOR CHAIR RESISTANCE / ESSAI DE LA CHAISE À ROULETTES
/ PROVA CON POLTRONA A ROTELLE / ROLWEERSTAND BUREAUSTOEL EN ISO 4918 - EN 425

EFFECT OF FURNITURE LEG / EFFECT DE PIED DE MEUBLE
/ EFFETTO DL GAMBE MOBILI / EFFECT VAN MEUBILAIR POTEN EN424

ELECTROSTATIC PERFORMANCE / POTENTIEL DE CHARGE ELECTROSTATIQUE
/ POTENZIALE DL CARICA ELETTROSTATICA / ELECTROSTATISCHE EIGENSCHAPPEN EN 1815

SLIP RESISTANCE / ANTIDÉPARANT / RESISTENZA ALLO SCIVOLAMENTO / SLIPWEERSTAND DIN 51130

WEAR RESISTANCE / RÉSISTANCE D'USURE / RESISTANCE ALL'USURA / SLIJTVASTHEID EN 660 -2

RESIDUAL INDENTATION / POINÇONNEMENT RÉMANENT
/ SENSIBILITÀ DL IMPRESSIONE / INDRUKBEVOELIGHEID EN ISO 24343-1

DIMENSIONAL STABILITY / STABILITÉ DIMENSIONNELLE
/ STABILITÀ DIMENSIONALE / DIMENSIONALE STABILITEIT EN434

FIRE RATING / CLASSIFICATION AU FEU / CLASSIFICAZIONE AL FUOCO / BRANDKLASSE EN ISO 9239-1

FORMALDEHYDE EMISSION / EMISSION DE FORMALDEHYDE
/ EMISSIONE DL FORMALDEIDE / FORMALDEHYDE EMISSIE EN717-1

WARRANTY FOR DOMESTIC USE / PÉRIODE DE GARANTIE USAGE DOMESTIQUE
/ GARANZIA PER USO DOMESTICO / GARANTIEPERIODE HUISHOUDELIJK GEBRUIK

WARRANTY FOR COMMERCIAL USE / PÉRIODE DE GARANTIE USAGE COMMERCIAL
/ GARANZIA PER USO COMMERCIALE / GARANTIEPERIODE COMMERCIEEL GEBRUIK

* valid for light commercial use as described by class 31

CLASSIC 5.0 MM

4 MM RIGICORE + 1.0 MM IXPE



5.0 MM



0.3 MM



CLASSE 31

PU

NATURAL

YES

178 X 1219 MM

2.168 SQM / 10 PLANKS

55 CARTONS / PALLET

1035 KG / 1075 KG



PASS



PASS



AVERAGE - 2.0 kV

R9/R10 DEPENDING ON EMBOSSING



GROUP T



PASS



PASS



BFL-S1



CLASS E1

15 YEARS

5 YEARS *